

PureHT™



SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	80-100 microns	Adhesive polyester	REACH n° 1907/2006/EU

APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends, Elastan (not suited for treated and dye sublimated textiles)	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	45°	60-80 gf	20 cm/sec	15 seconds	135°C (275°F)	medium (2,5/3,5 bar)	hot

- Cut the material mirrored
- Peel off excess material
- Place the decoration on the garment
- Apply following the recommended parameters
- Remove the carrier hot

PRODUCT HIGHLIGHTS

- COMPOSTABLE PRODUCT (after 180 days in the ground)
- No environmental impact
- 100% recyclable carrier

NOTE: We highly recommend to perform a test before launching a production.

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 40°C, inside-out	YES inside-out	YES (cycle: mixed synthetic/cotton)	No	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents

This document can be subject to variations.

